

SELECTION & SPECIFICATION DATA

Type	Fast Drying Asphalt Cutback
Description	Blackhawk 5157 is a coating that can be used for many purposes. This product has good corrosion and weather proof features. It also has excellent coverage and adhesion to marginly prepared surfaces. It is widely used to protect steel beams, steel pipes, and other metal parts. Blackhawk 5157 also functions well as a primer. Blackhawk 5157 has a very high solids content giving excellent coverage. It is supplied in the correct consistency for application and needs no thinning if kept air tight between uses.
Uses	Corrosion protection of: <ul style="list-style-type: none"> • Steel beams • Steel pipes • Engine chassis' Acts as an excellent primer for metal substrates.
Color	Black
Primer	Self-priming
Topcoats	Consult ErgonArmor
Finish	Gloss
Dry Film Thickness	3 – 5 mils
Solids Content	55% ± 5% by weight
Theoretical Coverage Rate	220 square feet per gallon at 4 DFT
VOC Value(s)	<450g/L, 3.75 lbs/gal

SUBSTRATES & SURFACE PREPARATION

All	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

MIXING & THINNING

Mixing	No mixing required. Ready to use as is.
Thinning	Do not thin

APPLICATION EQUIPMENT GUIDELINES

Airless Spray Single Leg or Pot	Pump Size 15:1 or greater Hose Length: 20 ft x 1/2 in ID
Brush	Apply with a wide fiber brush in order to create a smooth uniform film.
Roller	Use a low nap phenolic core roller.

CLEANUP & SAFETY

Cleanup	Mineral spirits
Safety	Read and follow all caution statements on this product data sheet and on the SDS for this product. Wear protective clothing, gloves and eye protection.
Ventilation	Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.

PACKAGING, HANDLING & STORAGE

Shelf Life	12 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
Storage Temperature & Humidity	40°F – 110°F (4°C – 43°C) 0 – 100% relative humidity
Storage	Store indoors. This product is not affected by excursions below these published storage temperatures, down to 10°F (-12°C), for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous and properly mixed.
Package Sizes & Shipping Weights	5 gallon (4.7 net fill) 55 gallon (53 net fill) 350 gallon carbon steel, returnable totes

Rev 06/19

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.