

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Polymer Modified Asphalt Emulsion
<b>Description</b>	A trowel and spray grade blend of polymer and emulsified asphalts that provide a tough, monolithic, rubberized waterproof fire retardant membrane on steel, cementitious, modified bitumen and other substrates.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Water-based with low VOCs</li> <li>• High elongation and tensile strength</li> <li>• Puncture resistant</li> <li>• Low permeation rates</li> <li>• Excellent chemical resistance</li> <li>• Sag resistant</li> <li>• Easily repairable</li> <li>• Flame spread resistant</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Waterproofing</li> <li>• Roofing</li> <li>• Moisture/vapor barrier</li> <li>• Secondary containment</li> <li>• Tank chime sealant</li> <li>• Retainage ponds</li> </ul>
<b>Color</b>	Black
<b>Finish</b>	Matte
<b>Primer</b>	Self-priming
<b>Dry Film Thickness (DFT)</b>	10 – 30 mils per coat
<b>Solids Content</b>	58% by weight 56% by volume
<b>Theoretical Coverage Rate</b>	898 square feet per gallon at 1 mil DFT
<b>Maximum Dry Temperature Resistance</b>	300°F (149°C)
<b>Limitations</b>	Protect from freezing

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	Surfaces must be clean and dry. Remove all dirt, dust, oil and all other contaminants.
<b>Previously Painted Surfaces</b>	Consult with ErgonArmor Technical Service Department.

## MIXING & THINNING

<b>Mixing</b>	Not required
<b>Thinning</b>	Do not thin
<b>Ratio</b>	Single component

## APPLICATION GUIDELINES

<b>Spray Application Guide</b>	Ertech 3137 is designed for brush, roller or airless spray equipment.
<b>Airless Spray</b>	For best results under a wide variety of spray conditions, a 30:1 or higher ratio pump is recommended.
<b>Tip Size</b>	A 0.025 in orifice tip size is recommended.
<b>Hose L/D</b>	200 ft (max) x 3/8 in diameter
<b>Whip L/D</b>	6 ft (max) x 1/4 in diameter
<b>Film Thickness</b>	A film thickness of up to 45 mils wet can be achieved on vertical surfaces without sagging.
<b>Brush/Roller</b>	Can be brush or roller applied.
<b>Temperature</b>	Use in temperatures of 50°F (10°C) or higher for best performance.
<b>Dry-To-Touch</b>	2 – 4 hours at 77°F (25°C). Cure times are shortened with air movement over the coating.
<b>Full Cure</b>	24 – 48 hours at 77°F (25°C). Cure times are shortened with air movement over the coating.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	6 months at 75°F (24°C) when kept at recommended storage conditions and in original unopened containers.
<b>Package Sizes &amp; Shipping Weights</b>	5 gallon pail – 47 lbs (21 kg) 16 gallon keg – 149 lbs (68 kg) 53 gallon drum – 501 lbs (227 kg)
<b>Storage Temperature</b>	50°F – 95°F (10°C – 35°C)
<b>Storage</b>	Protect from freezing. Do not store product outside. Store indoors.

## TYPICAL PHYSICAL PROPERTIES

Density ASTM D1475-13	8.7 lbs/gal
Solids by weight ASTM D5201-05a	58%
Solids by volume ASTM D5201-05a	56%
Specific gravity	1.04
Dry-to-touch, 77°F (25°C) ASTM D5895-96	2 – 4 hours
Full cure, 77°F (25°C)	24 – 48 hours
Viscosity, 77°F (25°C) ASTM D2983-19	75,000 cps
Resistance to oils, greases & solvents	Poor
VOC ASTM D3960-05	0.2 lbs/gal max
Permeance 60 mils nominal ASTM E96 A method	0.14 perms
Permeance 60 mils nominal ASTM E96 B method	0.08 perms
Hydrostatic pressure resistance 60 mils nominal ASTM C1306	39.2 psi
Low temperature crack bridging 60 mils nominal ASTM C836	Pass
Immersion test 60 mils nominal ASTM D870-09	Pass
Tensile strength ASTM D2370-16	87 psi
Elongation ASTM D412-16	>1, 573%

Rev 01/2020

### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).