



SELECTION & SPECIFICATION DATA

Type	Flexible Epoxy Coating
Description	This versatile, surface tolerant elastomeric industrial maintenance coating and joint compound offers moderate chemical resistance and outstanding adhesion to a wide variety of substrates including asphalt and concrete. Forms excellent barrier over sand, dirt or rock when applied to suitable geotextiles.
Features	<ul style="list-style-type: none"> • 100% solids, no VOCs • Excellent impact resistance • Excellent flexibility, >300% elongation • Moderate chemical resistance
Uses	<ul style="list-style-type: none"> • Crack-bridging base coat • Expansion joint filler • Crack filler • Secondary containment lining • Liner over earth and geotextile
Color	Light gray, blue
Finish	Gloss
Dry Film Thickness (DFT)	15 – 20 mils per coat on horizontal surfaces 6 – 10 mils on vertical surfaces
Solids Content	100% by volume

SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants
Steel	<p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 – 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 3 Commercial Blast with angular profile of 1.5 – 3.0 mils, SSPC-SP 2 Hand Tool or SSPC-SP 3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>
Concrete or Concrete Masonry Unit (CMU)	Concrete must be cured a minimum of 7 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with SSPC-SP 13/NACE 6. Required surface profile is CSP 3-5. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days. Prime with Novocoat SC1100 Primer/Sealer.
Previously Painted Surfaces	Consult with ErgonArmor Technical Service Department

MIXING & THINNING

Ratio	1 part resin to 1 part hardener by volume
Mixing	Mix equal parts of the resin and hardener thoroughly until color of material is uniform and free of streaks.
Thinning	Do not thin.
Pot Life	<p>40°F (4°C) 3 hours</p> <p>75°F (24°C) 2 hours</p> <p>92°F (33°C) 1 hours 30 minutes</p> <p>Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.</p>
Cleanup	MEK

APPLICATION GUIDANCE

Spray Application Guide	The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.
Airless Spray Plural Component	Contact ErgonArmor Technical Service for guidance.
Airless Spray Single Leg or Hot Pot	<p>Tip Size: 0.021-inch</p> <p>Pump Size: 56:1 or greater</p> <p>Output: 3500 – 5500 psi, filter removed</p> <p>Hose Length: 50 ft x 3/8-inch ID</p> <p>Whip Length: 6 – 10 ft x 1/4-inch ID</p> <p>Part A resin and Part B hardener should be heated individually before mixing so product will atomize properly in delivering paint to the substrate. Mixed product should be sprayed within 20 minutes after mixing.</p>
Brush/Roller	Can be brush or roller applied. Be aware of work life when using brush or roller application.

CURE SCHEDULE & RECOAT WINDOW

Recoat window at 75°F (24°C)	24 hours
Tack free at 75°F (24°C)	48 hours
Light traffic at 75°F (24°C)	7 days
Full cure at 75°F (24°C)	7 days

SAFETY

Safety	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
Ventilation	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.



PACKAGING, ESTIMATING & HANDLING

Package Sizes

Light Gray, 2 gal (7.6 L) Kit
 - Part A Resin Light Gray, 1 gal (3.8 L) Pail
 - Part B Hardener, 1 gal (3.8 L) Pail
 Item #: M-ER1010-2GLBK-01

Blue, 2 gal (7.6 L) Kit
 - Part A Resin Blue, 1 gal (3.8 L) Pail
 - Part B Hardener, 1 gal (3.8 L) Pail
 Item #: M-ER1050-2GLBK-01

Light Gray, 10 gal (38 L) Bulk Unit
 Order Parts A and B separately
 - Part A Resin Light Gray, 5 gal (18.9 L) Pail
 Item #: M-ER1010A-5GLB-01
 - Part B Hardener Clear, 5 gal (18.9 L) Pail
 Item #: M-ER1000B-5GLB-01

Blue, 10 gal (38 L) Bulk Unit
 Order Parts A and B separately
 - Part A Resin Blue, 5 gal (18.9 L) Pail
 Item #: M-ER1050A-5GLB-01
 - Part B Hardener Clear, 5 gal (18.9 L) Pail
 Item #: M-ER1000B-5GLB-01

Theoretical Coverage

267 square feet per gallon at 6 mils
 80 square feet per gallon at 20 mils
 Allow for loss in mixing and application.

Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with ErgonArmor.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE
Flash point	>240°F (115°C)
Impact strength at 80°F (26.5°C)	65 ft-lb
Tensile strength	287 psi
VOC	0 g/l
Elongation	>300%
Specific gravity	Resin: 1.44 Hardener: 0.97

SERVICE TEMPERATURE

SERVICE	MAXIMUM TEMPERATURE
Dry	200°F (93°C)
Splash/spill	200°F (93°C)
Immersion service	150°F (66°C)

Temperature limitations will vary with chemical exposure. Consult ErgonArmor Technical Service for guidance.

Rev 03/2021

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see ergonarmor.com.